




LUX LINE CO

NEW

JEO PREMIUM

HOMOGENEOUS FLOORING



Jeoflor®
AUSTRIA

JEO PREMIUM

NEW




34-43



6301




6315



6302



6316



6317



6303



6318



6314



6313






6322




6323



6308




6305



6324



6325



6306



6326



6327







34-43




JEO PREMIUM ^{NEW}




6319




6309




6320



6310



6311



6312



6307




6321



6304





LCA

Eco-designed according to a product specific Life Cycle Analysis



INDOOR AIR QUALITY

TVOC emissions 100 times better than norm requirements (TVOC < 10 µg/m³ after 28 days)



WELLNESS

Walking comfort < 75dB



RECYCLABILITY

100%



COMPOSITION

100% REACH compliant



RECYCLED CONTENT

25%

TECHNICAL SPECIFICATIONS

NEW
JEO PREMIUM

DESCRIPTION			
Total thickness	EN 428	mm	2.0
Weight	EN 430	g/m ²	3100
Width of sheet	EN 426	m	2
Length of sheet	EN 426	lm	20
CLASSIFICATION			
European classification	EN 685		34-43
Fire rating	EN ISO 9239-1 EN ISO 11925-2	Class	Bfl-s1
Toxic testing	GB 18586-2001		Good
Static electrical propensity	EN 1815	KV	≤ 2 Antistatic
Electrical resistance / Anti Static	EN 1081	Ω	10 ⁹ -10 ¹⁰
Slip resistance	DIN 51130	Class	R9
PERFORMANCES			
Dimensional stability	EN 434	%	≤ 0.4
Thermal conductivity	EN 12524	W/(m.k)	0.25
Castor wheel test	EN 425	-	OK
Wear resistance	EN 660.2	mm ³	≤ 2.0
Abrasion Group	EN 649	group	P
Type binder content	ISO 10581	type	I
Residual group	EN 433	mm	~ 0.02
Colour fastness	EN 20 105 B02	degree	≥ 6
Chemical product resistance	EN 423	class	OK
Antibacterial property MRSA	ISO 22196	-	>99% inhibits growth
Flexibility	ISO 8690	-	Good
Decontamination rated	EN 435	-	Very good
Impact sound reduction	EN ISO 10140/1		
	EN ISO 717/2	-	Approx.+4DB
Surface treatment		UV Protected	PUR+
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000 - 6	µg/m ³	<10
CE MARKING			
		EN 14041	   

The implementation of an effective cleaning regime defence against infections.



LUX LINE CO

Address : 8-1-523/300, Brindavan Colony, Tolichowki, Hyderabad 500008, Telangana, India.

Phone: +91 7680075590,

Email: info@luxlineco.com



Jeoflor®

Alptahls GmbH, Bürgergasse 4, 8330 Feldbach, Austria.

Tel. +43 (0)3152 370 49

info@Jeoflor.com www.Jeoflor.com

TollFree : 18002028498